

SUPERSOFT DOPPIO

**Coloured acrylic resin and rubber granules
based elastic coating for tennis courts**

CHARACTERISTICS

Supersoft Doppio is an intermediate covering for tennis courts. Specially selected rubber granules and quartz sand ensure excellent playing comfort and reduce traumas. Together with the special finish Top Doppio, the Supersoft Doppio system is a versatile and complete tennis court system, tested by the ITF (International Tennis Federation) in Speed Class 3 (medium).

APPEARANCE

Grey high-viscosity paste.

CHARACTERISTICS OF THE LIQUID PRODUCT

Characteristic	U.M.	Value	Tolerance
Specific weight	Kg/dm ³	1,51	± 0,1
Dry mass residue	%	75	± 3
Dry volume residue	%	63	± 3
Residue at 450°C	%	51	± 3
Brookfield viscosity (with Brookfield viscosimeter rotor no. 5, speed 20)	mPa·s	30000	± 2000
pH	-	8	± 1

LAYING INSTRUCTIONS

Tools	Thinner	Type of thinner	Cleaning tools
Rubber spatula	Approx. 30 %	Water	Water

LAYING SURFACE

Supersoft Doppio is developed above all for asphalt decks (see deck preparation instructions) following pre-treatment with Softbase; for application on cement deck please consult the Technical Office of Casali S.p.A.

IMPORTANT: resin surfaces are generally waterproof (non-draining) so that the deck must be sloped correctly to ensure rainwater runoff and prevent pooling. Works to correct the deck must be carried out before laying the final covering; if necessary please contact the Technical Office of Casali S.p.A.

CONSUMPTION

The minimum recommended coverage of the product as is on bituminous mat plugged with Softbase is 1.5 kg/sq.m. applied in 3 - 4 coatings, if possible crossing the coatings.

APPLICATION INSTRUCTIONS

Ambient temperature: MIN 10°C - MAX 40°C
Ambient relative humidity: MAX 90 %
Laying surface temperature: MIN 5°C - MAX 50°C

SPORTS SURFACES

SUPERSOFT DOPPIO

DATA SHEET

DRYING AT 23°C AND R.H. OF 50%

On surface	1 h
To touch	2 h
Interval between coatings	4 h

The times indicated refer to standard laboratory conditions. Curing times are strongly affected by weather conditions; high temperatures and direct sunlight accelerate curing; shade, low temperatures and high levels of humidity slow down curing. In winter, lay the product in the warmer hours of the day. Always allow the coating to dry perfectly before applying the next coating.

PACKAGING INSTRUCTIONS

Colours available	Grey.
Packaging	40 kg. drums.

STORAGE INSTRUCTIONS

Storage temperature:	MIN 3°C - MAX 40°C
Stability in the original package:	12 months

IMPORTANT INSTRUCTIONS

Do not apply the product in the case of fog, high humidity levels, rain or frost. The conditions of the deck must be checked to ensure that it is plane, resistant, consistent that the granule grading is correct in order to prevent imperfections on the surface. Repairs and/or filling must be carried out according to the specifications of Casali S.p.A. Check for rising dampness and/or infiltrations, if necessary contact the Technical Office of Casali S.p.A.

SAFETY STANDARDS

Please read the safety data sheet carefully before using this product.

*The data provided by these data sheets are approximate and the Company reserves the right to modify the same for technical reasons, without prior notice. The solutions proposed do not represent all the possible uses but are merely case studies deriving from Casali's installation experience and are therefore intended only for purposes of illustration. The user is exclusively responsible for the way the products illustrated are used, whether properly or improperly, for evaluating in advance the suitability or otherwise of the product for its requirements and exerting the utmost caution in handling chemical products. **Important: to ensure best colour uniformity of surface laid products, we recommend that you use materials from the same production lot as finishing layer. The Technical Office of Casali's Synthetics Division is at your complete disposal for any further specific information or explanations you may require (phone 071 9162095).***

CASALI
SPORT



Rev. 02/2018